

# Hydrotech® Monolithic Membrane 6125®

formerly known as Monolithic Membrane 6125®



BUILDING TRUST



## GENERAL DESCRIPTION

Hydrotech's Monolithic Membrane 6125 is a highly modified rubberized asphalt with 40% post-consumer recycled content (minimum 30% recycled content for REACH compliant material).

## BASIC USE

Hydrotech's Monolithic Membrane 6125 is specifically designed to be used as a roofing and/or waterproofing membrane typically on concrete substrates in vertical or horizontal applications such as roof decks, parking decks, reflecting pools, plazas, mechanical room sub-floors, foundation walls, tunnels and planters.



## SIZES

Hydrotech's Monolithic Membrane 6125 is available in recyclable cardboard cartons containing individual 40 pound cakes of material.

## TECHNICAL DATA

PROPERTY	TEST METHOD	RESULTS
FLASH POINT	ASTM D-92 CGSB-37.50-M89	≥500°F (260°C)*
PENETRATION	ASTM D-5329 CGSB-37.50-M89	98 mm @77°F (25°C) 187mm @122°F (50°C)
FLOW	ASTM D-5329 CGSB-37.50-M89	1.0 mm @140°F (60°C)
TOUGHNESS	CGSB-37.50-M89	16.0 Joules
RATIO OF TOUGHNESS TO PEAK LOAD	CGSB-37.50-M89	0.069
WATER VAPOR PERMEABILITY	ASTM E-96, Procedure E CGSB-37.50-M89	0.3 ng/Pa(s)m <sup>2</sup>
WATER ABSORPTION	CGSB-37.50-M89	0.11 gram weight gain
LOW TEMPERATURE FLEXIBILITY (-25°C)	CGSB-37.50-M89	No delamination, adhesion loss or cracking
LOW TEMPERATURE CRACK BRIDGING (-25°C)	CGSB-37.50-M89	No cracking, adhesion, loss or splitting
HEAT STABILITY	CGSB-37.50-M89	No change in viscosity, penetration, flow or low temperature flexibility
VISCOSITY	CGSB-37.50-M89	11.0 seconds
WATER RESISTANCE (5 days @ 50°C)	CGSB-37.50-M89	No delamination, blistering, emulsification or deterioration
SOFTENING POINT	ASTM D-36	180°F (82°C)
ELONGATION	ASTM D-5329	1000% minimum

\*or alternatively not less than 77°F (25°C) above the manufacturer's maximum recommended application temperature.  
(values published are min. req)

PROPERTY	TEST METHOD	RESULTS
RESILIENCY	ASTM D-5329	40% minimum
BOND TO CONCRETE	ASTM D-5329	Pass @0°F (-18°C)
ACID RESISTANCE	ASTM D-896 Procedure 7.1 (N-8)	Pass - 50% Nitric Acid - 50% Sulfuric Acid
RESISTANCE TO HYDROSTATIC PRESSURE	ASTM D-08.22, Draft 2 (developed: D5385)	100 psi (= 231 foot head of water)
RESISTANCE TO SALT WATER (20% sodium carbonate and calcium chloride)	ASTM D-896 similar	No delamination, blistering, emulsification or deterioration
RESISTANCE TO FERTILIZER (undiluted 15/5/5 nitrogen/phosphorus/potash)	ASTM D-896 similar	No delamination, blistering, emulsification or deterioration
RECYCLED CONTENT	U.L. Validated	40% post-consumer (30% REACH compliant)
RESISTANCE TO ANIMAL WASTE	3 year exposure	No deterioration
SOLIDS CONTENT		100%
SHELF LIFE		10 years (sealed)
SPECIFIC GRAVITY		1.15 + 0.02

**LEED INFORMATION**

	Credit 4	Credit 5
Recycled Content (% by weight)	40	
Manufacture Location		Montreal, QC
Extraction/Harvesting Location		Montreal, QC
VOC Content (g/L)		0

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.